OSYRIS DWL 3550





APPLICATIONS

- Solvent-based fluid for corrosion protection specifically developed to present:
 - superior water displacement capability
 - medium-term protection
 - short drying time
 - very low odor.

SPECIFICATIONS

• OSYRIS DWL 3550 complies with Standard ISO 6743/8 (1987): REE category.

ADVANTAGES

- OSYRIS DWL 3550 is specifically designed for corrosion protection in the metal processing industry:
- OSYRIS DWL 3550 is specifically developed to have a very low odor.
- OSYRIS DWL 3550 presents a superior water displacement capability.
- OSYRIS DWL 3550 coats the metal surface with a thin, soft and non drying protective film.
- OSYRIS DWL 3550 provides protection for about six months during indoor storage and for about two months during outdoor and sheltered storage.
- OSYRIS DWL 3550 presents a short drying time.
- OSYRIS DWL 3550 can be easily applied:
 - with a brush
 - by spraying
 - by immersion
- OSYRIS DWL 3550 can be easily removed with:
 - diluted alkaline detergents
 - solvents (liquid or vapour phase)
 - mechanical treatments.

TYPICAL CHARACTERISTICS	METHODS	UNITS	OSYRIS DWL 3550
Aspect	-	-	Clear
Density (@ 15°C)	EN ISO 12185	kg/m³	785
Flash Point	EN ISO 2719	°C	62
Viscosity (@ 40°C)	DIN 51562	mm ² /s	1.7
Thickness of film	-	μm	1.4

Above characteristics are mean values given as an information.

